

Durastrength® 510

Multifunctional Acrylic Impact Modifier

PRODUCT DESCRIPTION

Durastrength® 510 acrylic impact modifier imparts excellent impact properties and faster fusion to rigid vinyl products at lower acrylic use levels. Based on the unique chemistry of Durastrength® 200 impact modifier, which has been the leading impact modifier used in exterior durable building products for over 35 years, Durastrength® 510 impact modifier offers outstanding room and low-temperature impact in combination with unsurpassed ease of processing. The unique properties of Durastrength® 510 impact modifier make it especially suitable for vinyl siding and fence substrate formulations where high filler levels and high production rates put maximum stress on the formulation. Due to its unique process aid functionality, Durastrength® 510 impact modifier eliminates the need for added process aid in formulations that it is used to modify.

This efficiency typically enables a reduction in total acrylic level needed in most formulations.

TYPICAL PHYSICAL PROPERTIES*

Physical Form	White powder
Specific Gravity	1.09
Bulk Density	0.50 g/cc
Particle Size	10% Max on 50 Mesh
Percent Volatiles	1.2% Max

*Typical properties not to be construed as specifications

PRODUCT BENEFITS

1. For today's high output extrusion and large extruders, the low melt viscosity and fusion promoting characteristics of Durastrength® 510 impact modifier allows for smooth processing and excellent impact properties at low use levels, even when the formulation contains high levels of filler.
2. Durastrength® 510 impact modifier has been extensively tested for long-term weather resistance, retaining excellent impact resistance and color. Similar weathering benefits are seen in translucent applications.
3. The chemical composition of Durastrength® 510 impact modifier imparts excellent low-temperature impact.
4. The wide processing window of Durastrength® 510 impact modifier assures a consistently flawless surface finish.

PACKAGING

Durastrength® 510 impact modifier is packaged in 20 kg bags and 1000 lb. bulk bags.

STARTING FORMULATION RECOMMENDATIONS

Rigid Siding Capstock

PVC Resin (K-65 to K-67)	100.0 phr
Butyl Organotin Stabilizer	0.8 – 1.2
Calcium Stearate	1.0 – 1.5
Paraffin Wax (165°F mp)	1.0 – 1.5

Durastrength® 510 Impact Modifier	4.0 – 6.0
Plastistrength® 770 Process Aid	0.0 – 0.5
Titanium Dioxide	9.0 – 10.0

Rigid Siding Substrate

PVC Resin (K-65 to K-67)	100.0 phr
Butyl Organotin Stabilizer	0.8 – 1.2
Calcium Stearate	1.0 – 1.5
Paraffin Wax (165°F mp)	1.0 – 1.5
Oxidized Polyethylene Wax	1.0 – 0.2

Durastrength® 510 Impact Modifier	4.0 – 5.0
Calcium Carbonate (0.7µm)	0.0 – 1.0
Titanium Dioxide	2.0 – 5.0

Window Profile

PVC Resin (K-65 or K-67)	100.0 phr
Methyl Organotin Stabilizer	1.0 – 1.5
Internal Lubricant	1.0 – 1.2
External Lubricant	1.0 – 1.5
Oxidized Polyethylene Wax	1.0 – 0.2
Durastrength® 510 Impact Modifier	5.0 – 6.0
Plastistrength® 770 Process Aid	0.5 – 1.5
Calcium Carbonate (0.7µm)	0.0 – 5.0
Titanium Dioxide	9.0 – 10.0

SUGGESTIONS FOR USE

Durastrength® 510 impact modifier is recommended for applications such as vinyl siding and window profiles where good outdoor weathering and impact resistance are critical properties. Durastrength® 510 impact modifier shows excellent processability, leading to optimized fusion and impact properties at reduced loadings of total acrylics.

Customers should evaluate Durastrength® 510 impact modifier in their own laboratories to establish optimum conditions for use in their processes and applications. Arkema's Technical Service Team is available to discuss your application requirements, provide formulation guidance and laboratory testing as needed.

ENVIRONMENTAL AND SAFETY INFORMATION

Before handling this material, read and understand the Safety Data Sheet (SDS) for additional information on handling, storage, and disposal of the product to ensure the health of users, the safety of facilities, and the protection of the environment. The SDS is available on our website www.arkema.com or upon request at our Customer Service Department. Arkema believes strongly in Responsible Care® as a public commitment.

MORE TECHNICAL INFORMATION AVAILABLE

Ask your Arkema account manager for further information on high quality Arkema additives for use in PVC, PC, PBT, ABS, PLA, epoxies, (meth)-acrylics, and other thermoplastic or thermosetting systems. Arkema produces a full line of impact modifiers and processing aids. In addition, Arkema's Technical Service staff is also available to assist compounders and processors with formulation and processing recommendations.

Durastrength® Impact Modifiers

Durastrength® acrylic impact modifiers deliver outstanding impact characteristics for outdoor durable applications in PVC, engineering resins and thermosets.

Plastistrength® Process Aids

Plastistrength® process aids offer producers a complete line of melt strengtheners and metal release agents for PVC and engineering resins. Plastistrength® process aids can improve fusion, surging, and aesthetics.

Biostrength® Additives

Biostrength® impact modifiers are designed to improve properties and enhance processability of polylactic acid (PLA) and other biopolymer compounds.

FOR MORE INFORMATION CONTACT

Please contact your local account manager, our headquarters, or our R&D centers:

Global Headquarters

Arkema
Arkema Coating Resins
LIGHTWELL Building
51 Esplanade du Général de Gaulle
CS 10478 - 92907 Paris La Défense cedex
France
Tel: +33 (0)1 49 00 80 80
plasticadditives.arkema.com/en/contact/

US Headquarters

Arkema Inc.
Arkema Coating Resins
410 Gregson Dr.
Cary, NC 27511
Tel: +1 (877) 331-6696
plasticadditives.arkema.com/en/contact/

US R&D Center

Arkema Inc.
900 1st Avenue
King of Prussia, PA 19406
Tel: +1 (610) 878-6500
plasticadditives.arkema.com/en/contact/

Visit
plastic.additives.arkema.com



ASK QUESTIONS
TO OUR EXPERTS



LIBRARY
DOCUMENTS
WEBINARS



WEB SERVICES
TDS
SAMPLING



INTERACTIVE
PRODUCT FINDERS
& BROCHURES

Plastistrength® is a registered trademark of Arkema. Biostrength® and Durastrength® are registered trademarks of Arkema Inc. Responsible Care® is a registered trademark of the American Chemistry Council Inc. 2026 Arkema Inc. All rights reserved.

Please consult Arkema's disclaimer regarding the use of our products on
<http://www.arkema.com/en/products/product-safety/disclaimer/>

ARKEMA

plasticadditives.arkema.com